



Durez 118 Black Phenolic is a two-stage, general purpose molding material. It exhibits improved impact strength and resistance to flexural fatigue for demanding automotive, electrical and appliance applications. Shrinkage and mechanical strengths are closely controlled to meet part reliability requirements.

Revision Date Jul 10, 2017

Plasticities available for compression, transfer, and injection molding.

Form of Material Granular Feeding & Preforming Good Storage Life One Year

PHENOLIC

Typical Properties		Compression		Injection Grade	
		International Units	English Units	International Units	English Units
Physical	Specific Gravity (D792)	1.40	1.40	1.40	1.40
	Apparent Density (D1895)	0.58 g/cc	0.58 g/cc	0.58 g/cc	0.58 g/cc
	Molding Shrinkage* (D6289)	0.007 m/m	0.007 in/in	0.0110 m/m	0.0110 in/in
	Water Absorption (D570)	0.50 %	0.50 %	0.50 %	0.50 %
Mechanical	Tensile Strength (D638)	55 Mpa	8,000 psi	48 Mpa	7,000 psi
	Flexural Strength (D790)	76 Mpa	11,000 psi	69 Mpa	10,000 psi
	Compressive Strength (D695)	207 Mpa	30,000 psi	207 Mpa	30,000 psi
	Tensile Modulus (D638)	9.6 Gpa	1.4 x10 ⁶ psi	8.3 Gpa	1.2 x10 ⁶ psi
	Izod Impact (D256)	18.1 J/m	0.34 ft lb/in	16.5 J/m	0.31 ft lb/in
Thermal	Deflection Temperature (D648)	171 °C	340 °F	149 °C	300 °F
	UL Flammability (UL-94) @	1.5 mm	HB	1.5 mm	HB
		For complete UL Listing for this material refer to the UL web Site www.ul.com	3.0 mm	V - 1	3.0 mm
	UL Temperature Index (Elect) @	6.0 mm	V - 0	6.0 mm	V - 0
Electrical	Dielectric Strength (D149)				
	Short Time	15.7 MV/m	400 V/mil	8.8 MV/m	225 V/mil
	Step by Step	13.8 MV/m	350 V/mil	6.9 MV/m	175 V/mil
	Dissipation Factor (D150)1 MHZ	.05	.05	.06	.06
	Dielectric Constant (D150)1 MHZ	4.7	4.7	5.5	5.5
Volume Resistivity(ohms)(D257)	10.0 x10 ¹⁰ m	10.0 x10 ¹² cm	0.1 x10 ¹⁰ m	0.1 x10 ¹² cm	

Properties determined with test specimens molded at 340-350°F *Typical transfer-molded shrinkage is 0.009 in/in or m/m

Other Properties

ASTM D-5948 (former Mil-M-14G), Type CFG certification requires batch testing

RoHS2 (2011/65/EU) Compliant
REACH (EC 1907/2006) SVHC / Annex XIV Compliant
HR4173 Sec.1502 Conflict Materials Compliant
Halogen Free

Shelf life- Minimum one year at typical ambient conditions.

IMPORTANT! The information presented herein, while not guaranteed, was prepared by technical personnel and is true and accurate to the best of our knowledge. No warranty or guaranty, expressed or implied is made regarding performance stability or otherwise. This information is not intended to be all inclusive as the manner and conditions of use, handling, storage, and other factors may involve other or additional safety or performance considerations. While our technical personnel will be happy to respond to questions regarding safe handling and use procedures, safe handling and use remains the responsibility of the customer. No suggestions for use are intended as and nothing herein shall be construed as a recommendation to infringe any existing patents or violate any Federal, State or local laws.

Sumitomo Bakelite North America, Inc.
Corporate Office and Technical Market Development Center
46820 Magellan Drive, Suite C, Novi, MI 48377
Tel. 1-248-313-7000

www.sbhpp.com

Durez Canada Company Ltd.
100 Dunlop Street, P.O. Box 100
Fort Erie, Ontario L2A 5M6
Tel. 1-905-346-8700