



## Technical Data Sheet

---

### **Durez® 13037** phenolic resin

#### Description:

Durez® 13037 is a viscous thermoplastic phenolic resin that requires the addition of hexamethylenetetramine to get thermosetting properties. It is recommended as a softener in compounding NBR stocks and will impart reinforcement to these stocks during vulcanisation in conjunction with the added hexamine.

#### Typical properties:

Test method	Properties	Durez® 13037
DCT 1	Appearance	dark brown liquid
DCT 61	Solution Viscosity at 25°C, (4/1 resin/acetone ),cps	900

\* DCT test methods are available upon request

[www.sbhpp.com](http://www.sbhpp.com)

SBHPP | HIGH PERFORMANCE PLASTICS BUSINESS UNIT OF SUMITOMO BAKELITE CO., LTD.

SUMITOMO BAKELITE EUROPE N.V. – HENRY FORDLAAN 80 – 3600 GENK - BELGIUM  
TEL.: +32 (0)89 320 311 | FAX: +32 (0)89 320 309 | E-MAIL: INFOSBE@SUMIBE.EU

RPR TONGEREN – BTW/VAT / BE 0403 125 169



## Technical Data Sheet

---

### Storage:

Durez<sup>®</sup> 13037 is a stable material at ambient temperatures. When stored under optimum storage conditions ( below 20°C and 60% relative humidity in unopened original packaging ), Durez<sup>®</sup> 13037 has a shelf life of 12 months from the shipping date.

### Packaging:

Standard packaging for Durez<sup>®</sup> 13037 is 220L coated steel drums, containing 190Kg net. All packaging is marked with product number, lot number and net weight.

**READ THE MATERIAL SAFETY DATA SHEET BEFORE HANDLING, STORING OR USING THIS PRODUCT.**

The information presented herein, while not guaranteed, is to the best of our knowledge true and accurate. No warranty or guarantee express or implied is made regarding the performance or stability of any product, since the manner of use and conditions of storage and handling are beyond our control. No suggestion for product use nor anything contained herein shall be construed as a recommendation for its use in infringement of any existing patent.

[www.sbhpp.com](http://www.sbhpp.com)

SBHPP | HIGH PERFORMANCE PLASTICS BUSINESS UNIT OF SUMITOMO BAKELITE CO., LTD.

SUMITOMO BAKELITE EUROPE N.V. – HENRY FORDLAAN 80 – 3600 GENK - BELGIUM  
TEL.: +32 (0)89 320 311 | FAX: +32 (0)89 320 309 | E-MAIL: [INFOSBE@SUMIBE.EU](mailto:INFOSBE@SUMIBE.EU)

RPR TONGEREN – BTW/VAT / BE 0403 125 169