

Unclad glass epoxy lamnetes for polishing & lapping carrier

| Test item | Condition | Unit | EL-3700 Test data : 1.0mmt | EL-3700M Test data : 1.0mmt |
|------------------------------|-----------------|----------|-------------------------------------|--------------------------------|
| Color | A | - | Natural | Natural |
| Thickness | A | - | 0.4 - 2.0 | 0.2 - 1.0 |
| Insulation resistance | A | Ω | 2E+11 | 4E+10 |
| | D-2/100 | Ω | 9E+10 | 3E+10 |
| Flexural strength | Lengthwise | MPa | 650 | 740 |
| | Widthwise | MPa | 540 | 580 |
| Hardness | Rockwell | HRM | 110 | 110 |
| Water absorption | E-24/50+D-24/23 | | 0.08 | 0.08 |
| Flame retardancy (UL method) | A | - | V-0 equivalent | V-0 equivalent |
| | F-168/70 | | | |
| Size | A | mm | 1020*1020 1200*1200 1220*1220 | |

*The data mentioned above is not guaranteed value but representative.